

List of UL-Styles (Multicore cables)

UL-Style No.	Insulation Material	Voltage Volt	Temp. °C	Insulation thickness mm	AWG Size	UL-Style No.	Insulation Material	Voltage Volt	Temp. °C	Insulation thickness mm	AWG Size
2006	PVC	300	80	1,14	20 - 16	2464	variable	300	80	-	-
2007	PVC	300	90	1,14	20 - 16	2468	PVC	300	80	0,38	32 - 16
2012	PVC	300	80	1,52	18 - 16	2474	PVC	600	105	-	26 - 16
2015	PVC	300	80	1,52	18 - 16	2477	PVC	600	60	-	33 - 16
2030	PVC	600	80	1,91	14 - 10	2483	PVC	600	105	-	26 - 16
2031	PVC	600	90	1,91	14 - 10	2489	PVC	600	60	-	18
2032	PVC	600	105	1,91	14 - 10	2490	AWM	not specified*	60	AWM	min. 36
2089	PVC	300	60	-	20 - 18	2493	PP	600	60	-	30 - 16
2090	PVC	300	60	-	20 - 18	2498	PE	300	80	-	28 - 16
2091	PVC	300	60	-	20 - 18	2501	PVC	600	105	-	30
2092	PE	300	60	-	26 - 16	2502	variable	30	80	-	-
2093	PE	300	60	-	26 - 16	2504	PVC	600	105	-	20 - 14
2094	PE	300	60	-	26 - 16	2507	PVC	600	60	-	26 - 16
2095	PVC	300	90	-	32 - 16	2516	PVC	600	105	-	30 - 9
2096	PVC	300	80	-	30 - 16	2517	PVC	300	105	-	32 - 16
2097	PVC	300	80	-	30 - 18	2532	PVC	30	60	-	30 - 16
2098	PVC	300	90	-	26 - 16	2535	PVC	30	80	-	30 - 16
2099	PVC	300	90	-	26 - 16	2548	PE	300	80	-	-
2100	PVC	300	90	-	26 - 16	2549	PVC	300	90	-	30 - 16
2101	PVC	300	105	0,38	30 - 16	2550	AWM	600	90	AWM	min. 40
2102	PVC	300	105	-	30 - 16	2551	AWM	30	105	AWM	min. 40
2103	PVC	300	105	0,38	30 - 16	2560	PVC	30	60	-	30
2106	PE	600	60	-	26 - 12	2564	PVC	125	75	-	22
2107	PE	600	60	-	26 - 12	2567	PVC	600	60	-	-
2108	PE	600	60	-	26 - 12	2570	PVC	600	80	-	30 - 9
2112	PVC	300	80	0,38	26 - 16	2571	PVC	-	80	-	30 - 16
2113	PVC	300	80	0,38	26 - 16	2574	AWM	30	105	AWM	min. 40
2114	PVC	300	80	0,38	26 - 16	2576	PVC	150	80	-	30 - 9
2115	PVC	600	80	-	26 - 16	2582	PE	150	60	-	30 - 16
2116	PVC	600	80	-	26 - 16	2584	PVC	125	80	-	30 - 9
2117	PVC	600	80	-	26 - 16	2586	PVC	600	105	-	30 - 9
2121	PVC	300/600	90	0,38	26 - 16	2587	PVC	600	90	-	30 - 9
2122	PVC	300/600	90	0,38	26 - 16	2589	AWM	30	105	AWM	see AWM Requirements
2123	PVC	300/600	90	0,38	26 - 16	2598	VAR	300	60	-	30 - 16
2124	PVC	600	90	0,76	28 - 9	2606	PE	300	60	-	30
2125	PVC	600	90	0,76	28 - 9	2610	see 1007 labeled Style	300	80	labeled Style 1007	see 1007 Requirements
2126	PVC	600	90	0,76	28 - 9	2614	AWM	30	105	AWM	min. 40
2127	PVC	600	105	0,76	28 - 9	2623	PE	30	80	-	30 - 20
2128	PVC	600	105	0,76	29 - 9	2626	AWM	30	80	AWM	not specified*
2129	PVC	600	105	0,76	28 - 9	2629	PE	300	80	-	30 - 16
2243	PVC	300	105	1,14	20 - 16	2630	AWM	125	90	AWM	30 - 9
2261	PVC	300	105	0,76	18	2631	AWM	not specified*	90	AWM	min. 40
2262	PE	600 (isol.)	60	0,76	26 - 16	2637	AWM	30	90	AWM	min. 40
2263	PE	300 (Jacket) 600 (isol.)	60	0,76	26 - 16	2653	AWM	600	90	AWM	36 - 6
2264	PE	300 (Jacket) 600 (isol.)	60	0,76	26 - 16	2654	AWM	300	90	AWM	36 - 6
2265	PVC	300 (Jacket) 300	80	0,38	26 - 16	2655	PVC	300	80	-	33 - 10
2266	PVC	300	80	-	26 - 16	2656	AWM	600	80	AWM	36 - 6
2267	PVC	300	80	-	36 - 30	2660	AWM	not specified*	60	AWM	-
2268	PVC	300	80	-	26 - 16	2661	AWM	300	105	AWM	36 - 6
2269	PVC	300	80	-	26 - 16	2662	PVC	600	105	-	33 - 10
2270	PVC	300	80	-	26 - 16	2668	AWM	30	60	AWM	min. 40
2271	as for SVT	300	60	as for SVT	26 - 16	2678	PVC	30	105	-	-
2272	as for SVT	300	60	as for SVT	26 - 16	2704	PVC	30	60	-	30
2273	as for SVT	300	60	as for SVT	26 - 16	2778	AWM	150	60	AWM	30 - 16
2274	as for SVT	300	60	as for SVT	26 - 16	2789	AWM	30	60	AWM	see AWM
2275	as for SVT	300	60	as for SVT	26 - 16	2833	AWM	30	60	AWM	-
2276	as for SVT	300	60	as for SVT	26 - 16	2835	PP	30	80	-	22
2277	as for SVT	300	60	as for SVT	26 - 16	2919	PP	30	80	-	28 - 18
2278	as for SVT	300	60	as for SVT	26 - 16	2920	AWM	30	60	AWM	min. 40
2279	as for SVT	300	60	as for SVT	26 - 16	2921	AWM	30	60	AWM	min. 40
2280	as for SVT	300	60	as for SVT	26 - 16	2930	AWM	not specified*	105	AWM	min. 40
2317	PE	600	60	-	26 - 16	2951	AWM	125	105	AWM	min. 40
2351	PE	600	80	-	26 - 16	2937	AWM	300	80	AWM	AWM
2352	PE	300	80	-	26 - 16	3071	S/GB	600	200	0,76	18 - 14
2353	PE	300	80	-	26 - 16	3075	S/GB	600	200	0,76	10 - 2
2354	PE	600	80	-	26 - 16	3173	XLPE	600	125	0,76	26 - 9
2355	PE	600	80	-	26 - 16	3199	XLPE	300	105	0,38	22 - 16
2376	PVC	300	105	-	-	3212	SIR	600	150	1,14	26 - 10
2384	variable	30	60	-	30	3213	SIR	600	150	1,52	8 - 2
2385	VAR	30	60	-	30	3214	SIR	600	150	1,91	1 - 4/0
2386	VAR	30	60	-	30	3239	SIR	VAR	150	VAR	24 - 10
2387	VAR	30	60	-	30	3265	XLPE	150	125	0,25	28 - 20
2388	PVC	30	60	-	-	3266	XLPE	300	125	0,38	26 - 16
2405	PVC	300	80	-	30 - 16	3271	XLPE	600	125	VAR	24 - 12
2439	PE	600	80	-	26 - 16	3272	XLPE	600	125	VAR	22 - 4
2448	variable	30	60	-	30	3291	XPVC	300	105	-	26 - 16
2461	PVC	30	60	-	26 - 16	20063	PE	300	80	0,5	28 - 16
2462	PVC	300	60	-	-	20083	PE	300	80	AWM	diverse AWM
2463	PVC	600	80	-	26 - 10	20601	AWM	300	80	AWM	AWM

* not specified